

Grease for Tire Mold Lubrication

Product Information

Krytox™ TM7 grease is specifically designed for the lubrication of segmented molds, both electrically and steam-heated, in the vulcanization process of rubber tire manufacturing. This lubricant eliminates carbon residue buildup on the molds associated with hydrocarbon and hydrocarbon-based synthetic greases. Krytox™ TM7 exhibits excellent adhesion, allowing the operator to significantly increase production by extending lubrication intervals. Krytox™ TM7 will last in excess of 5,000 cycles, based on average curing times, without re-lubrication.

Krytox™ TM7 grease is a fluorinated grease with polytetrafluorethylene (PTFE) thickener and selected additives. It has excellent thermal stability and load-carrying abilities. Krytox™ TM7 has a high degree of chemical inertness and extremely high hydrolytic stability. Contact with boiling water or steam has no effect.

Typical Properties*	Krytox™ TM7
Standard NLGI Grade	2
Estimated Useful Temperature Range, °C (°F)	-20 to 290 (-4 to 555)
Pour Point, °C (°F)	-25 (-13)
Base Oil Viscosity, cSt	
20 °C (68 °F)	1,715
40 °C (104 °F)	500
100 °C (212 °F)	46
Oil Volatility, % in 22 hr, 260 °C (500 °F), D972 Modified	<1
Appearance	White, Creamy Consistency
Specific Gravity	2.0

*These values are typical properties and not product specifications.

The information set forth herein is furnished free of charge and based on technical data that Chemours believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. The handling precaution information contained herein is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Because conditions of product use are outside our control, Chemours makes no warranties, express or implied, and assumes no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF CHEMOURS.

For product information, industry applications, technical assistance, or global distributor contacts, visit krytox.com or within the U.S. and Canada, call 1-844-773-CHEM/2436 or outside of the U.S., call 1-302-773-1000.

© 2017 The Chemours Company FC, LLC. Krytox™ and any associated logos are trademarks or copyrights of The Chemours Company FC, LLC. Chemours™ and the Chemours Logo are trademarks of The Chemours Company.

Replaces: H-93780-4

C-11337 (6/17)